Product present		4			email : <u>info@cfpflex.com</u> site : <u>www.cfpflex.com</u>	SOLVENT FREE VEGAN
100% Made in Fra	HEET			Date: 16/05/2023		
PRODUCT	UNIFLEX® ##		Diamond	Plotter	film with diamond rainbow effect for heat transfer on textiles	
CODES	100D		COLOURS RAINBOW		BOW	
DESCRIPTION	Water based polyurethane coating, with diamond rainbow effect, laminated between a non-adhesive polyester carrier and a heat adhesive layer.					
THICKNESS (+/-5%)	Heatadhesive polyurethane: 70 microns. Non-adhesive Carrier film: 100 microns.					
TEXTILES	Cotton - Polyester - Polycotton					
ADVANTAGES	 Quick weeding Quick pressing time at low temperature: 140°C/10 seconds on cotton, polyester, polycotton Universal thermoadhesive with excellent bonding on most textiles. Washing resistance: cold wash Elastic and strong polyurethane, doesn't wrinkle after washings. Pleasant non-adhesive carrier, easy to stack and handle. Ecofriendly, water based, solvent and PVC free polyurethane. Low carbon profile manufacturing: all operations made under one roof. Hundred per cent made in France, out of european raw materials. 					
	10. Last generat	on machines and exclusive manufacturing process, ensuring competitive prices.				
PRESSURE		Medium (depending upon the characteristics of the press)				
PEELING		COLDPEEL				
HEATPRESSING:		140°C/10 seconds.				
WITHOUT OVERLAPPING		Washing temperature: cold wash				
2. Always baking pa FURTHER 3. Wait 24 RECOMMANDATIONS 4. Do not 5. Iron fro		2. Always p baking pape 3. Wait 24 h 4. Do not us 5. Iron from	itable for very small letters protect Flex material from direct contact with heating plate with a release oper, in order to avoid any possible lifting at press opening. 4 hours before washing. use bleach or other aggressive chemical agents. om inside. our products in a tempered and dry room, protected from direct sun rays.			
			components, REACH compliant, without PVC, plastifiers, VOC, according			
			x Standard 100 Class 1.			
RESUBLIMATION UNIFLEX D		UNIFLEX DI	IAMOND can be applied on sublimated polyester.			
It blocks co			lors migration from the textile			
image or te Peel off car			r cutting with scissors or by plotter, and weeding of contours, place the ext directly on garment, set the iron on medium heat. Don't use any vapour. rier when cool.			
This document is likely to be modified without notice. Please take contact with our commercial department.						